

## ELIT G NATURAL



L'articolo NATURAL veste un ruolo di primo piano nella categoria dei rivestimenti di alta qualità. Il suo stesso nome, NATURAL, racchiude le due caratteristiche peculiari e fondamentali della pelle stessa: NATURALEZZA e MORBIDEZZA. Con uno spessore che varia tra 1.3 e 1.5 mm e un processo di concia molto accurato e ricco di componenti rivitalizzanti, il NATURAL si presenta con una mano molto morbida che dona una gradevolissima sensazione tattile. Grazie ad un accurato trattamento del fiore e all'utilizzo di pigmenti ecologici (o a base d'acqua) selezionati si riesce ad ottenere una pelle con uno strato protettivo molto leggero e resistente ed un aspetto brillante e naturale. Una caratteristica molto importante, che lo differenzia da quasi tutti i pellami per arredamento, è la totale assenza di un processo meccanico di stampa. La grana, che naturalmente monta sul NATURAL, proviene dal processo di lavorazione a cui è sottoposto ed è tipica delle pelli in pieno spessore. Il tutto ottenuto nel più grande rispetto della natura e dell'uomo.

The item NATURAL has a great role in the category of high-quality coverings. The name itself expresses the main and fundamental characteristics of the leather: NATURELESS and SOFTNESS. With its thickness which varies from 1.3 to 1.5 mm and an accurate retanning process, rich in revitalizing components, NATURAL introduces itself with its very soft hand which gives a pleasant tactile sensation. Thanks to an accurate processing of the grain and to the use of selected ecological (or containing water) pigments, it is possible to obtain a leather with a very light and resistant protection layer, with a brilliant and natural aspect. This NATURAL results to be particularly pleasant and give pleasant silky and warm sensation from the very first touches. Its main characteristic which distinguishes it from almost all furniture leathers is the complete lack of mechanical printing processes: the natural grain on NATURAL derives from the working process to which it is submitted, typical of the full-thick leathers. This process is carried on in the full respect for man and the environment.

### CARATTERISTICHE / CHARACTERISTICS

**SPESSORE / THICKNESS**

1.3/ 1.5 mm

**ORIGINE MATERIA PRIMA / ORIGIN OF THE RAW MATERIALS**

Bovine Europee

**TIPO DI CONCIA / TANNING TYPOLOGY**

Al Cromo / Chrome

**TIRATURA / DYE**

Tintura Passante / Feedthrough dye

**TIPO DI RIFINIZIONE / FINISHING**

Fiore anilina con oli e cere naturali

Aniline grain with natural oils and waxes

### TEST FISICI / PHYSICAL TEST

**RESISTENZA ALLO STROFINIO A UMIDO IUF 450**

RESISTANCE AGAINST WET RUBBING IUF 450

100 cicli / cycles

**RESISTENZA ALLO STROFINIO A SECCO IUF 450**

RESISTANCE AGAINST DRY RUBBING IUF 450

500 cicli / cycles

**FATICA ALLA FLESSIONE / BENDING FATIGUE**

30000 flessioni / bendingd

**SOLIDITÀ ALLA LUCE / SOLIDITY AT LIGHT**

min. 3

**CIGARET TEST**

bs 5852-1/ 79



4001



4009



4002



4003



4004



4005



4006



4007



4008



4010



4011



4012



4013



4014